

Material Data

Data listed below are only for reference. Data can be adjusted in order to meet special requirement

	GS 11	GS 12	GS 13	GS 14	GS 15
Thickness	2mm	2mm	1mm	1mm	1mm
Wavelength	%T	%T	%T	%T	%T
200	0.00	0.00	0.00	0.00	0.00
220	0.00	0.00	0.00	0.00	0.00
240	0.00	0.00	0.00	0.00	0.00
250	0.00	0.00	0.00	0.00	0.00
260	0.00	0.00	0.00	0.00	0.00
280	0.00	0.00	0.00	0.00	0.00
300	0.00	0.00	0.00	0.00	0.00
320	0.00	0.00	0.00	0.00	0.00
340	0.00	0.00	0.00	0.00	0.00
350	0.00	0.00	0.00	0.00	0.00
360	0.00	0.00	0.00	0.00	0.00
380	0.00	0.60	0.00	0.00	0.00
400	0.00	14.70	0.00	0.00	0.00
420	0.00	35.40	0.00	0.00	0.00
440	3.00	47.40	0.10	0.10	0.00
450	6.60	54.70	0.40	0.20	0.00
460	12.00	61.90	1.20	0.50	0.00
480	30.30	71.80	4.90	2.00	0.40
500	51.30	77.10	13.80	5.60	1.40
520	63.40	81.20	20.00	10.00	2.90
540	67.90	83.10	22.90	11.50	3.60
550	67.00	83.50	22.00	11.00	3.40
560	64.50	83.90	20.40	10.00	3.10
580	54.70	83.10	14.50	8.10	2.50
600	42.30	82.00	8.30	5.20	1.60
620	30.40	80.50	4.10	2.30	0.70
640	25.30	79.80	2.40	1.50	0.40
650	23.00	79.80	2.10	1.30	0.30
660	21.30	79.80	1.70	1.20	0.40
680	20.50	80.90	1.90	1.60	0.60
700	20.80	81.20	1.80	1.60	0.90
720	22.00	82.80	1.90	1.10	1.20
740	24.10	84.30	2.00	1.00	1.50
750	25.30	85.10	2.20	1.00	1.50
760	26.40	85.90	2.30	1.00	1.50
780	29.00	87.10	2.40	1.10	1.30
800	29.00	87.90	2.40	1.20	1.20
840	30.30	88.70	2.70	1.40	1.30
880	31.80	89.10	3.10	1.70	1.60
920	34.80	89.50	3.80	2.10	2.10
960	38.20	89.50	4.30	2.70	2.50
1000	41.90	89.50	4.50	3.10	3.00