

Material Data

Data listed below are only for reference. Data can be adjusted in order to meet special requirement

	GS 16	GS 17	GS 18	GS 19
Thickness	2mm	2mm	2mm	2mm
Wavelength	%T	%T	%T	%T
200	0.00	0.00	0.00	0.00
220	0.00	0.00	0.00	0.00
240	0.00	0.00	0.00	0.00
250	0.00	0.00	0.00	0.00
260	0.00	0.00	0.00	0.00
280	0.41	0.00	0.00	0.00
300	21.96	0.00	0.00	0.00
320	53.08	0.00	0.00	0.00
340	66.61	0.00	0.00	0.00
350	67.91	0.00	0.00	0.00
360	67.28	0.00	0.00	0.00
380	56.60	0.00	0.00	0.20
400	38.19	0.00	0.00	0.50
420	22.43	0.00	1.05	1.30
440	14.09	0.10	6.89	2.00
450	13.22	1.40	12.97	2.40
460	13.82	9.90	20.55	2.90
480	20.11	29.40	37.38	6.20
500	37.00	60.10	50.86	8.00
520	60.28	68.90	62.88	8.00
540	77.24	73.70	60.58	4.00
550	81.54	69.30	55.58	2.00
560	83.57	63.10	49.58	1.00
580	82.01	51.60	32.91	0.00
600	74.93	41.10	18.33	0.00
620	62.99	32.30	10.00	0.00
640	49.54	24.60	5.42	0.00
650	43.44	21.00	4.08	0.00
660	38.30	19.20	3.76	0.00
680	31.55	16.80	3.17	0.00
700	29.14	16.00	2.51	0.00
720	30.79	16.40	2.32	0.00
740	35.80	16.40	2.16	0.00
750	39.37	16.80	2.01	0.00
760	43.47	17.20	1.99	0.00
780	52.75	17.50	2.15	0.00
800	62.06	17.60	2.18	0.00
840	76.36	18.00	2.55	0.00
880	83.18	19.20	5.17	0.00
920	85.87	20.10	7.58	0.20
960	86.65	24.60	9.77	0.40
1000	86.56	28.50	12.28	0.40

